

Registered seat: Čermenská 910, 749 01 Vítkov CZ

Facility: paper mill Aloisov, 789 63 Ruda nad Moravou

Alveolar carton	PN 17-158-10
	ČJK 516

This company regulation is applicable for manufacture, testing and deliveries of alveolar carton, used for manufacture of paper and textile cavities, or other purposes.

1. GENERAL INFORMATION

1.1. Definition of basic terms

1.1.1. Carton is a product with grammage of 150 g/m² a or more.

1.1.2. Alveolar carton is made of pulp and waste paper in two variations (type A and PYROS).

2. TECHNICAL INFORMATION

2.1. General information

2.1.1. Cartons are made in white or are coloured, machine glazed or unglazed.

2.1.2. Cartons have to be evenly processed, flat and without any creases, overlap marks holes, curtains, ruptures and without any other mechanical damage.

2.1.3. The carton must not contain rough impurities protruding to their surface, insufficiently debonded, waste paper, tar or oily stains or remains of unsolved dye.

2.2. Acceptable deviations

2.2.1. Only sporadic defects inside the reels, which are not noticeable during the rewinding process, like imperceptible lap marks and curtains and similar in amount. not exceeding 2% of max. weight of the delivery.

2.2.2. Paper and carton contains remains of impurities from the waste papers and color shades

2.2.3. The wiewthrough of the paper might be cloudy (nebulous).

2.3. Qualitative parameters

2.3.1. Qualitative parameteres of the paper and carton have to correspond with the values stated in the summary sheet number 1.

Summary sheet number 1 - cartons

Qualitative parameters	Unit of measure	A (alveolar carton)	PYROS	Testing norm
Grammage	g/m ²	160 - 250	170 - 190	ČSN EN ISO 536
Allowed tollerance up to 230 g/m ²		+ - 4 %		
over 230 g/m ²		+ - 8 %		
Index of the strength in tension limit, lengthwise, min.	Nm/g	24,5	/	ČSN EN ISO 1924-2
Objemová hmotnost	g/m ³	0,7	/	ČSN ISO 534
Water absorbtion according to Cobb	g/m ²	20 - 90	20 - 70	ČSN ISO 535
Brace strength across, min.	kN/m	1,2	1,6 - 1,7	ČSN 50 0350
Smoothness, min.	s	/	18	ČSN ISO 5627
Moisture	%	4 - 8		ČSN ISO 287

(Different parameters of carton may be concluded in sales contract.)

2.4. Dimensions and quality

2.4.1. The Carton must not change its colour or release the color from its surface when exposed to moisture or steam at the temperature of 100°C

2.4.2. Papers and cartons are produced in the reels, sheets and leaflets. The reels are produced in the width and diameter as agreed.

2.4.3. Acceptable dimension deviation

- a) reels:
- 1) width
 - acceptable tolerance is $\pm 5\%$
 - but maximum $\pm 3\text{mm}$ (for the reels wider than 60 cm)
 - but minimum $\pm 2\text{mm}$ (for the reels narrower than 40 cm)
 - If the customer requests compliance of the maximum and minimum width the tolerance will double.
 - 2) diameter
 - without the indication of the maximum and minimum diameter size obtains the tolerance from -4 cm up to $+2\text{ cm}$
 - with the indication of the minimum diameter size is the tolerance $+4\text{ cm}$
 - with the indication of the maximum diameter size is the tolerance -6 cm
- b) sheets
- 1) length and width of the format A3&A4 $\pm 0,2\%$ from the dimension, by others maximum $\pm 2\text{mm}$
 - 2) vertically a maximum $0,2\%$ from the dimension, however a maximum of 2 mm .

2.4.4. Winding of the reels

- a) Number of the reel ruptures
- The diameter of the reel till 60cm - the paper web can be ruptured at maximum 2x
 - The diameter of the reel above 70cm - the paper web can be ruptured at maximum 3x

b) the performance of the patch-up

The performance of the patch-up has to be fast and clean without any patch-up of the contiguous layers.

The patched-up place has to be able to pass through the manufacturing machine without any problems.

The patch-up place has to be visibly marked at the coils of the reels by coloured line or by sticking coloured pieces of paper according to the customer wish.

3. TESTING

3.1. The samples for testing are taken according to the norm ČSN EN ISO 186.

3.2. The average sample, from which are the sample sheets taken, is climatized according to the norm ČSN ISO 187.

3.3. The paper attributes are determined according to valid norms, which are stated in the relevant summary sheet.

The dimensions of the reels and sheets are checked by the steel measuring instruments according to the norm ČSN 25 11 04.

4. PACKING, LABELLING, TRANSPORT AND STOCKING

4.1. Packing and signification

4.1.1. The packing and labelling of the paper is done in accordance to internal regulations of the producer, unless agreed otherwise. All products (reels, sheets) which are dispatched from the plant have to be protected against atmospheric changes and have to stay packed till the production process is finished.

4.1.2. The product is labelled by the manipulation sign „ PROTECT AGAINST THE RAIN“ according to the norm ČSN EN ISO 780.

4.1.3. The package of the product is marked in accordance with Act, number 477/2001 Sb., On packages, and ČSN 77 0052-2, Waste Packages, Identification sign for the evaluation.

4.2. Transport and stocking

4.2.1. Papers and cartons are delivered in the enclosed, dried and cleaned means of the transport, which are ensured against the movement and the damage with the usual way of the transport.

4.2.2. Paper is stored in the enclosed, cleaned, dried and ventilated rooms, has to be protected against direct climatic influences, ground moisture, radiating heat and against dirt and pollution.

To ensure optimal stocking conditions it is recommended to keep the relative moisture between 40 - 60 % and the temperature 20-25 °C.

4.2.3. Reaching the thermal balance between the stocking area and the printer. The paper has to reach the thermal balance before it goes through the printing process. The required period depends on the amount of the paper and on the atmospheric conditions, see the summary sheet number 3.

The summary sheet number 2 – The period of the thermal balance establishment

Paper quantity		Temperature difference between the stocking area and the printer.				
		5°C	10°C	20°C	30°C	35°C
m3	kg	The period for the establishment of the thermal balance in hours				
0,4	320	9	17	36	64	92
0,6	480	10	20	42	76	106
1,0	800	11	23	46	84	115

Producer:

Company name:

MELECKY a.s.**Facility: Paper Mill Aloisov, Ruda nad Moravou CZ.****Registered seat at: Čermenská 910, Vítkov CZ.****IČO : 25904019**

Effective date:

1-st of September 2010

Obchodní firma:

MELECKY a.s.**Provozovna: Papírna Aloisov, Ruda nad Moravou****Sídlo: Čermenská 910, Vítkov****IČO : 25904019**

Účinnost:

od 1.9.2010